

Carrier		
Film Type	PET Film with waterproof coating	
Thickness (mil)	4.9 mil	
Gloss	>100	Dr. Lange Reflektometer, 20° measuring angle
Adhesive		
Adhesive Type	Ultra clear silicone adhesive	
Adhesive Strength (90°, gf/in)	>7	ASTM D3759
Release Liner		
Type	Siliconized white PET liner	
Nominal Thickness (mil)	2 mil	
Weight (g/m2)	70	
Other		
Handling/Storage Conditions	18 to 25 C / 64 to 77 F; 40 to 65% relative humidity	
Indoor Conditions for Processing	18 to 25 C / 64 to 77 F; 40 to 65% relative humidity	
End Use Temperature Range	-40 to 65 C / -40 to 149 F	

Advantages / Special Features

- Unique silicone adhesive is both removable and repositionable
- May be reverse printed for inside mounted window advertising
- UltraClear PET can be installed dry, however, a wet-method of installation is recommended to minimize bubbles.

Process & Handling

- To avoid fingerprints, handle the film with cotton gloves when loading and unloading the film on your printer.
- When printing with high ink density, it is not recommended to use the take up reel of your printer.
- Allow prints to dry for 24 hours before lamination and/or installation.
- Profiles can be found at <http://seal-us.color-base.com>. Check the site for profile availability for your particular printer and RIP software combination. If a profile is not found for your printer and RIP combination, try using a profile for backlit film.
- Prior to application, clean and dry the window, avoiding ammonia based cleaners.

Ink Compatibility	
Solvent	◆
Eco-Solvent	◆
Latex	◆
UV-Curable	◆

For Technical Support with any of our inkjet print materials, please call SEAL Media Support at 800-257-7325, ext 8945.



October 2013

Temperatures and thicknesses are given as approximate values. All data are standard values. The information in this specification sheet is based on findings obtained in practice. Because of the high number of factors which can have an effect during handling and application, customer tests will be required. A legally binding guarantee of specific properties is not to be inferred from our specifications. The information given here may be subject to change without notice. SEAL has not prepared MSDSs for these products which are not subject to the MSDS requirements of the Occupational Safety and Health Administration's Hazard Communication Standard, 29 C.F.R 1910.1200(b)(6)(v). When used under reasonable conditions or in accordance with the SEAL directions for use, these products should not present a health and safety hazard. However, use or processing of the products in a manner not in accordance with the directions for use may affect their performance and present potential health and safety hazards. The purchaser should test material to determine if it is suitable for their own specific purpose.